

APPLICATION OF THIAZOLE AND TRIAZOLE COMPOUNDS IN CARBON  
STEEL CORROSION PROTECTION

ASIAH MOHAMAD

A dissertation submitted in fulfillment of the  
requirements for the award of the degree of  
Master of Science (Chemistry)

Faculty of Science  
Universiti Teknologi Malaysia

OCTOBER 2009

*To mak, ayah, family and friends...*

## ACKNOWLEDGMENT

First and foremost I would like to express my sincere appreciation to Prof. Dr. Rahmalan Ahamad as my project supervisor for his encouragement, guidance, critics and friendship. Without his continued support and interest, this dissertation would not have been the same as presented here. He is always guiding me in doing my research and writing this dissertation and may Allah bless all his sacrifices and efforts.

My special appreciation also goes to all friends who have helped and give me their support whenever I need them. Their help and encouragement is very useful in finishing my project and report writing. I am also grateful to all my family members for their morale support and encouragement. Lastly, my thanks also go to everyone who has supported me all the way.

Thank you.

## ABSTRACT

Inhibitory effect of 2-mercaptobenzothiazole (MBT) and 1,2,3-benzotriazole (BTA) on corrosion of carbon steel in 1.0 M HCl and seawater sample respectively has been studied using weight loss method. All measurements show that inhibition efficiencies of BTA and MBT increased with increase in inhibitor concentration and temperature in 1.0 M HCl and seawater sample. The results of the investigation show that the compound BTA and MBT have fairly good inhibiting properties with inhibition efficiencies of 98.24% for BTA and 92.98% for MBT in seawater sample while 87.49% for BTA and 30.15% for MBT in 1.0 M HCl, at 90 °C. Adsorption of these inhibitors follows the Langmuir adsorption isotherm. Thermodynamic adsorption parameters ( $K_{ads}$ ,  $\Delta G_{ads}$ ) of BTA and MBT were calculated using the Langmuir adsorption isotherm. The adsorptions of BTA and MBT on carbon steel are spontaneous processes in 1.0 M HCl and seawater sample, indicated by the negative values of  $\Delta G_{ads}$ .

## ABSTRAK

Kesan hambatan oleh 2-mercaptobenzothiazol (MBT) dan 1,2,3-benzotriazol (BTA) terhadap pengaratan keluli karbon dalam larutan asid hidroklorik (HCl) 1.0 M dan sampel air laut telah dikaji menggunakan teknik pengurangan berat. Berdasarkan analisis yang dilakukan, kecekapan hambatan oleh BTA dan MBT terhadap pengaratan keluli karbon di dalam HCl 1.0 M dan sampel air laut meningkat dengan peningkatan kepekatan bahan hambatan dan suhu medium rendaman. Hasil kajian menunjukkan BTA dan MBT mempunyai ciri-ciri hambatan kakisan yang agak bagus dengan kecekapan hambatan sebanyak 98.24% untuk BTA dan 92.98% untuk MBT di dalam sampel air laut manakala 87.49% untuk BTA dan 30.15% untuk MBT di dalam HCl 1.0 M pada suhu 90 °C. Proses penjerapan kedua-dua bahan hambatan kakisan tersebut di dalam HCl 1.0 M dan sampel air laut adalah mematuhi isoterma penjerapan Langmuir. Parameter penjerapan termodinamik iaitu pemalar penjerapan ( $K_{ads}$ ) dan tenaga bebas Gibbs ( $\Delta G_{ads}$ ) telah dikira mengikut persamaan isoterma penjerapan Langmuir. Hasil kajian termodinamik memberikan nilai  $\Delta G_{ads}$  yang negatif menunjukkan proses penjerapan bahan hambatan BTA dan MBT ke atas keluli karbon di dalam HCl 1.0 M dan sampel air laut adalah spontan.

## TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	<b>DECLARATION OF POSTGRADUATE PROJECT PAPER</b>	
	<b>SUPERVISOR'S DECLARATION</b>	
	<b>TITLE PAGE</b>	i
	<b>DECLARATION OF ORIGINALITY</b>	ii
	<b>DEDICATION</b>	iii
	<b>ACKNOWLEDGEMENTS</b>	iv
	<b>ABSTRACT</b>	v
	<b>ABSTRAK</b>	vi
	<b>TABLE OF CONTENTS</b>	vii
	<b>LIST OF TABLES</b>	x
	<b>LIST OF FIGURES</b>	xii
	<b>LIST OF SYMBOLS</b>	xiv
	<b>LIST OF ABBREVIATIONS</b>	xv
<b>1</b>	<b>INTRODUCTION</b>	
	1.1 Background of Study	1
	1.2 Statement of Problem	3
	1.3 Research Objectives	3
	1.4 Scope of Study	4
<b>2</b>	<b>LITERATURE REVIEW</b>	
	2.1 Basic Concept of Corrosion	5
	2.2 Types of Corrosion	7

2.3 Corrosion Inhibitor	7
2.3.1 Anodic Passivating Inhibitors	9
2.3.2 Cathodic Inhibitors	9
2.3.3 Ohmic Inhibitors	10
2.3.4 Organic Inhibitors	10
2.3.5 Precipitation Inhibitors	11
2.3.6 Vapor Phase Inhibitors	12
2.4 Studies on Carbon Steel Corrosion Control	12
2.5 Commonly Used Corrosion Inhibitor	13
2.6 Thiazole Compounds as Corrosion Inhibitors	18
2.7 Weight Loss Method	19
<b>3 METHODOLOGY</b>	
3.1 Chemicals	20
3.2 Apparatus and Instrumentation	20
3.3 Preparation of Carbon Steel Coupon	21
3.4 Determination of Elemental Composition of Carbon Steel Coupons	21
3.5 Solutions Preparation	22
3.5.1 1,2,3-Benzotriazole (BTA) 0.5 M	22
3.5.2 2-Mercaptobenzothiazole (MBT) 0.5 M	23
3.5.3 Hydrochloric Acid (HCl) 1.0 M	23
3.5.4 Seawater Sample	23
3.6 Weight Loss Measurements	24
3.6.1 Inhibitor Concentration Effect	25
3.6.2 Immersion Period Effect	26
3.6.3 Temperature Effect	26
3.7 Microstructure Analysis of Coupons	27

<b>4</b>	<b>RESULTS AND DISCUSSION</b>	
	4.1 Determination of Elemental Composition of Carbon Steel Coupons	28
	4.2 Weight Loss Measurements	29
	4.2.1 Inhibitor Concentration Effect	29
	4.2.2 Immersion Period Effect	31
	4.2.3 Temperature Effect	33
	4.3 Corrosion Inhibition in Seawater Sample	34
	4.3.1 Inhibitor Concentration Effect	35
	4.3.2 Temperature Effect	36
	4.4 Adsorption Isotherms and Thermodynamics	38
	4.5 Microstructure Analysis of the Carbon Steel Coupons	41
<b>5</b>	<b>CONCLUSION AND FUTURE WORK</b>	
	5.1 Conclusion	44
	5.2 Future Work	45
	<b>REFERENCES</b>	46



**LIST OF TABLES**

<b>TABLE NO.</b>	<b>TITLE</b>	<b>PAGE</b>
2.1	Types of Corrosion	8
2.2	Summary on corrosion inhibitor application in various research areas	15
4.1	Elements composition of carbon steel coupons	28
4.2	Corrosion rate, surface coverage and inhibition efficiency for various concentration of BTA and MBT for the corrosion of carbon steel after 24 hours immersion in 1.0 M HCl obtained from weight loss measurements at 25 °C	30
4.3	Corrosion rate, surface coverage and inhibition efficiency for carbon steel after 1, 2, 4, 8, and 24 hours immersion in 1.0 M HCl with absence and presence of $10^{-2}$ M BTA and MBT respectively obtained from weight loss measurements at 25 °C	31
4.4	Corrosion rate, surface coverage and inhibition efficiency for various immersion temperature of carbon steel after 24 hours immersion in 1.0 M HCl with absence and presence of $10^{-2}$ M BTA and MBT respectively obtained from weight loss measurements	33
4.5	Corrosion rate, surface coverage and inhibition efficiency for various concentrations of BTA and MBT for the corrosion of carbon steel after 24 hours immersion in seawater sample obtained from weight loss measurements at 25 °C	35
4.6	Corrosion rate, surface coverage and inhibition efficiency for various immersion temperature of carbon steel after 24 hours immersion in seawater sample with absence and presence of $10^{-2}$ M BTA and MBT respectively obtained from weight loss measurements	37

4.7	Thermodynamic parameters obtained from weight loss measurements for the adsorption of BTA and MBT in 1.0 M HCl on the carbon steel at 25 °C	41
4.8	Thermodynamic parameters obtained from weight loss measurements for the adsorption of BTA and MBT in seawater sample on the carbon steel at 25 °C	41

## LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
1.1	Piece of gas pipeline with external corrosion	2
1.2	Ruptured gas pipeline due to corrosion	2
1.3	Structure of 1,2,3-benzotriazole (BTA)	3
1.4	Structure of 2-mercaptobenzothiazole (MBT)	4
3.1	Carbon steel coupons with dimensions 20mm x 20mm x 2.5mm used in weight loss measurements	21
3.2	Photograph of FESEM-EDX, model JSM-6701F	22
4.1	Variations of the inhibition efficiency calculated from weight loss measurements at different concentrations of BTA and MBT after 24 hours immersion in 1.0 M HCl solution at 25 °C	30
4.2	Variations of the inhibition efficiency of BTA and MBT calculated from weight loss measurements at different immersion period in 1.0 M HCl solution at 25 °C	32
4.3	Inhibition efficiency of BTA and MBT in 1.0 M HCl calculated from weight loss measurements at different immersion temperature for $10^{-2}$ M inhibitor concentration respectively	34
4.4	Inhibition efficiency calculated from weight loss measurements at different concentrations of BTA and MBT after 24 hours immersion in seawater sample at 25 °C	36
4.5	Inhibition efficiency of BTA and MBT in seawater sample calculated from weight loss measurements at different immersion temperature for $10^{-2}$ M inhibitor concentration respectively	37
4.6	Langmuir isotherm for adsorption of MBT and BTA on carbon steel surface in 1.0 M HCl at 25 °C	39

4.7	Langmuir isotherm for adsorption of MBT and BTA on carbon steel surface in seawater sample at 25 °C	40
4.8	Microstructure of carbon steel coupons	43

**LIST OF SYMBOLS**

$\Delta G_{\text{ads}}$	-	Free energy of adsorption
$^{\circ}\text{C}$	-	Degree Celsius
$\theta$	-	Degree of surface coverage
%	-	percent
$C$	-	Inhibitor concentration
$f$	-	Factor of energetic inhomogeneity
g	-	Gram
h	-	Hour
$K_{\text{ads}}$	-	Equilibrium constant of adsorption process
kg	-	Kilogram
M	-	Molar
mg	-	Milligram
$\text{mg cm}^{-2} \text{ h}^{-1}$	-	Milligram per centimeter square per hour
mL	-	Milliliter
mm	-	Millimeter
ppm	-	Part per million
$R^2$	-	Correlation coefficient

**LIST OF ABBREVIATIONS**

APM	-	Ammonium polymolybdate
ASTM	-	American Standard for Testing Materials Society
BTA	-	1,2,3-benzotriazole
EDX	-	Energy dispersive X-ray spectrometer
FESEM	-	Field emission scanning electron microscopy
GA	-	Gum Arabic
IE	-	Inhibition efficiency
MBT	-	2-mercaptobenzothiazole
MDEA	-	Methyldiethanolamine
PAE	-	<i>P. amarus</i> extract
PEG	-	Polyethylene glycol
PVC	-	Polyvinyl chloride
SAMs	-	Self assembled monolayers
VCI	-	Volatile corrosion inhibitor
VPI	-	Vapor phase inhibitor
ZPC	-	Zero point charge

## **CHAPTER 1**

### **INTRODUCTION**

#### **1.1 Background of Study**

Corrosion is a naturally occurring phenomenon commonly defined as the deterioration of a substance (usually a metal) or its properties because of a reaction with its environment (Delinder *et al.*, 1984). Like other natural hazards such as earthquakes or severe weather disturbances, corrosion can cause dangerous and expensive damage to everything from automobiles, home appliances, drinking water systems, pipelines, bridges, and public buildings (Treseder, 1991).

Corrosion is one of the major problems affecting the performance, safety and appearance of materials (Rim-rukeh *et al.*, 2006). In many industries, the need to use constructional materials safely, but cost effectively, is a primary consideration. Corrosion affects all areas of the economy and it has been estimated that the cost of corrosion represent 4% of the gross national product. These numbers include direct losses for replacement of corroded materials and equipment ruined by corrosion, indirect losses include cost of repair and loss of production, cost of corrosion protection and cost of corrosion prevention (Landolt, 2006).

Frequently, physical requirements can be satisfied easily, but corrosion effects seriously complicate the selection of suitable materials. Generally, increase corrosion resistance can only be obtained at increased cost. Despite continuing advances in corrosion resistant materials, the use of the chemical inhibitors often remains the most practical and cost effective means of preventing corrosion (Al-Sarawy *et al.*, 2008).

Figure 1.1 and Figure 1.2 show the examples of corrosion effect in which gas pipelines have been damaged by external corrosion.



**Figure 1.1:** Piece of gas pipeline with external corrosion (Thompson, 2001)



**Figure 1.2:** Ruptured gas pipeline due to corrosion (Thompson, 2001)




## 1.2 Problem Statement

The inhibition efficiency of organic compounds is strongly dependent on the structure and chemical properties of the layer formed on the metal surface under particular experimental conditions (El-Rehim *et al.*, 2001). It is also dependent on the state of the metal surface, type of corrosive medium, composition of the steel and the chemical structure of the inhibitor (Azhar *et al.*, 2001). Studies report that the adsorption of the organic inhibitors mainly depends on some physical-chemical properties of the molecule related to its functional group, as well as on the strength of the inhibitor–metal bond (Samide *et al.*, 2005). It is also necessary to investigate the effectiveness of inhibitors under severe conditions, such as acidic and sea water, that might occur to a carbon steel. To date, there is no report found in the literature regarding the use of 2-mercaptobenzothiazole and 1,2,3-benzotriazole for carbon steel inhibition under acidic and sea water conditions. Therefore, this study on inhibition of carbon steel corrosion by a thiazole and a triazole compounds was carried out.


## 1.3 Research Objectives

The objectives of this research are:

1. to investigate the inhibition efficiency of 1,2,3-benzotriazole (BTA) (Figure 1.3) and 2-mercaptobenzothiazole (MBT) (Figure 1.4) towards carbon steel in acidic and sea water conditions respectively,



**Figure 1.3:** Structure of 1,2,3-benzotriazole (BTA)



**Figure 1.4:** Structure of 2-mercaptobenzothiazole (MBT)

2. to study the effect of temperature on the corrosion rate and thermodynamic parameters related to the corrosion process,

#### **1.4 Scope of the Study**

This study was limited to the effects of 2-mercaptobenzothiazole (MBT) and 1,2,3-benzotriazole (BTA) as corrosion inhibitors for carbon steel corrosion protection under acidic and sea water conditions respectively. The technique applied in this study was a chemical technique that involved weight loss experiments. The study also involved elemental analysis of the carbon steel used and the microstructure of the carbon steel coupons with and without the application of inhibitors.

## REFERENCES

- Abdallah, M. (2004). Guar Gum as Corrosion Inhibitor for Carbon Steel in Sulfuric Acid Solutions. *Portugaliae Electrochimica Acta*. 22: 161-175.
- Ahamad, I. and Quraishi, M. A. (2009). Bis (benzimidazol-2-yl) disulphide: An Efficient Water Soluble Inhibitor for Corrosion of Mild Steel in Acid Media. *Corrosion Science*. 51: 2006-2013.
- Al-Sarawy, A. A., Foudab, A. S. and El-Dein, W. A. S. (2008). Some Thiazole Derivatives as Corrosion Inhibitors for Carbon Steel in Acidic Medium. *Desalination*. 229: 279-293.
- Alagta, A., Felhosi, I., Bertoti, I. and Kalman, E. (2008). Corrosion Protection Properties of Hydroxamic Acid Self-assembled Monolayer on Carbon Steel. *Corrosion Science*. 50: 1644-1649.
- Ali, S. A., Al-Muallem, H. A., Saeed, M. T. and Rahman, S. U. (2008). Hydrophobic-tailed Bicycloisoxazolidines: A Comparative Study of the Newly Synthesized Compounds on the Inhibition of Mild Steel Corrosion in Hydrochloric and Sulfuric Acid Media. *Corrosion Science*. 50: 664-675.
- Ali, S. A., Saeed, M. T. and Rahman, S. U. (2003). The Isoxazolidines: A New Class of Corrosion Inhibitors of Mild Steel in Acidic Medium. *Corrosion Science*. 45: 253-266.
- Aljourani, J., Raeissi, K. and Golozar, M. A. (2009). Benzimidazole and Its Derivatives as Corrosion Inhibitors for Mild Steel in 1M HCl Solution. *Corrosion Science*. 51: 1836-1843.
- Álvarez-Bustamante, R., Negrón-Silva, G., Abreu-Quijano, M., Herrera-Hernández, H., Romero-Romo, M., Cuán, A. and Palomar-Pardavé, M. (2009). Electrochemical study of 2-mercaptoimidazole as a novel corrosion inhibitor for steels. *Electrochimica Acta*. 54: 5393-5399.
- ASTM (2005). *A29M-05*. Philadelphia: American Society for Testing and Material.

- Atkinson, J. T. N. and Vandroffelaar, H. (1985). *Corrosion and Its Control: An Introduction to the Subject*. (1<sup>st</sup> ed.) Texas: National Association of Corrosion Engineers.
- Azhar, M. E., Mernari, B., Traisnel, M., Bentiss, F. and Lagranea, M. (2001). Corrosion Inhibition of Mild Steel by the New Class of Inhibitors [2,5-bis(n-pyridyl)-1,3,4-thiadiazoles] in Acidic Media. *Corrosion Science*. 43: 2229-2238.
- Behpour, M., Ghoreishi, S. M., Soltani, N., Salavati-Niasari, M., Hamadani, M. and Gandomi, A. (2008). Electrochemical and theoretical investigation on the corrosion inhibition of mild steel by thiosalicylaldehyde derivatives in hydrochloric acid solution. *Corrosion Science*. 50: 2172-2181.
- Benabdellah, M., Aouniti, A., Dafali, A., Hammouti, B., Benkaddour, M., Yahyi, A. and Ettouhami, A. (2006). Investigation of the Inhibitive Effect of Triphenyltin 2-thiophene Carboxylate on Corrosion of Steel in 2M H<sub>3</sub>PO<sub>4</sub> Solutions. *Applied Surface Science*. 252: 8341-8347.
- Benabdellah, M., Touzani, R., Dafali, A., Hammouti, B. and Kadiri, S. E. (2007). Ruthenium-ligand Complex, an Efficient Inhibitor of Steel Corrosion in H<sub>3</sub>PO<sub>4</sub> Media. *Material Letters*. 61: 1197-1204.
- Bentiss, F., Lebrini, M. and Lagranea, M. (2005). Thermodynamic Characterization of Metal Dissolution and Inhibitor Adsorption Process in Mild steel/ 2,5-bis(n-thienyl)-1,3,4-thiadiazoles/ hydrochloric acid system. *Corrosion Science*. 47: 2915-2931.
- Bosich, J. F. (1970). *Corrosion Prevention for Practicing Engineers*. (2<sup>nd</sup> ed.) New York: Barnes & Noble, Inc.
- Bouklah, M., Hammouti, B., Lagranea, M. and Bentiss, F. (2006). Thermodynamic Properties of 2,5-bis(4-methoxyphenyl)-1,3,4-oxadiazole as a Corrosion Inhibitor for Mild Steel in Normal Sulfuric Acid Medium. *Corrosion Science*. 48: 2831-2842.
- Chen, Y. H., Chang, C. Y., Chen, C. C., Chiu, C. Y., Yu, Y. H., Chiang, P. C., Ku, Y., Chen, J. N. and Chang, C. F. (2004). Decomposition of 2-mercaptothiazoline in Aqueous Solution by Ozonation. *Chemosphere*. 56: 133-140.
- Chilton, J. P. (1968). *Principles of Metallic Corrosion*. (1<sup>st</sup> ed). London: The Chemical Society.

- Clubley, B. G. (1988). *Chemical Inhibitors for Corrosion Control*. (1<sup>st</sup> ed). Manchester: Royal Society of Chemistry.
- Delinder, L. S. V., Dillon, C. P., Snoggrass, J. S. and Webster, H. A. (1984). *Corrosion Basics An Introduction*. (1<sup>st</sup> ed). Texas: National Association of Corrosion Engineers.
- Dillon, C. P. (1982). *Forms of Corrosion - Recognition and Prevention*. (1<sup>st</sup> ed). Texas: National Association of Corrosion Engineers.
- Dugstad, A., Nyborg, R. and Seiersten, M. (2003). Flow Assurance in pH Stabilised Wet Gas Pipelines. *Corrosion NACExpo*. Houston: Nace International.
- El-Rehim, S. S. A., Refaey, S. A. M., Taha, F., Saleh, M. B. and Ahmed, R. A. (2001). Corrosion Inhibition of Mild Steel in Acidic Medium using 2-amino thiophenol and 2-cyanomethyl benzothiazole. *Journal of Applied Electrochemistry*. 31: 429-435.
- Emergul, K. C. and Hayvali, M. (2006). Studies on the Effect of a Newly Synthesized Schiff Based Compound from Phenazone and Vanilin on the Corrosion of Steel in 2M HCl. *Corrosion Science*. 48: 797-812.
- Estevao, L. R. M. and Nascimento, R. S. V. (2001). Modifications in the Volatilization Rate of Volatile Corrosion Inhibitors by Mean of Host-guest Systems. *Corrosion Science*. 43: 1133-1153.
- Evans, U. R. (1981). *An Introduction to Metallic Corrosion*. (1<sup>st</sup> ed). London: Edward Arnold Limited.
- Fouda, A. S., Al-Sarawy, A. A. and El-Katori, E. E. (2006). Pyrazolone Derivatives as Corrosion Inhibitors for Carbonsteel in Hydrochloric Acid Solution. *Desalination*. 2001: 1-13.
- Fraunhofer, J. A. V. (1974). *Concise Corrosion Science*. (1<sup>st</sup> ed). London: Portcullis Press Limited.
- Gao, B., Zhang, X. and Sheng, Y. (2008). Studies on Preparing and Corrosion Inhibition Behaviour of Quaternized Polyethyleneimine for Low Carbon Steel in Sulfuric Acid. *Materials Chemistry and Physics*. 108: 375-381.
- Grillo, C. A., Mirífico, M. V., Morales, M. L., Reigosa, M. A. and Mele, M. F. L. D. (2009). Assessment of Cytotoxic and Cytogenetic Effects of a 1,2,5-thiadiazole Derivative on CHO-K1 cells. Its Application as Corrosion Inhibitor. *Journal of Hazardous Materials*. 170: 1173-1178.

- Harrop, D. (1988). *Chemical Inhibitors for Corrosion Control*. (1<sup>st</sup> ed). Manchester: Royal Society of Chemistry.
- Hassan, H. H. (2007). Inhibition of Mild Steel Corrosion in Hydrochloric Acid Solution by Triazole Derivatives Part II: Time and Temperature Effects and Thermodynamic Treatments. *Electrochimica Acta*. 53: 1722-1730.
- Khaled, F. K. and Al-Qahtani, M. M. (2009). The Inhibitive Effect of Some Tetrazole Derivatives Towards Al Corrosion in Acid Solution: Chemical, Electrochemical and Theoretical Studies. *Materials Chemistry and Physics*. 113: 150-158.
- Khaled, K. F. (2008). Molecular Simulation, Quantum Chemical Calculations and Electrochemical Studies for Inhibition of Mild Steel by Triazoles. *Electrochimica Acta*. 53: 3484-3492.
- Khaled, K. F. and Amin, M. A. (2009). Corrosion Monitoring of Mild Steel in Sulphuric Acid Solutions in Presence of Some Thiazole Derivatives – Molecular Dynamics, Chemical and Electrochemical Studies. *Corrosion Science*. 51: 1964-1975.
- Khaled, K. F., Fadi-Allah, S. A. and Hammouti, B. (2009). Some Benzothiazole Derivatives as Corrosion Inhibitors for Copper in Acidic Medium: Experimental and Quantum Chemical Molecular Dynamics Approach. *Materials Chemistry and Physics*. 117: 148-155.
- Kvarekval, J. and Dugstad, A. (2006). Corrosion Mitigation with pH Stabilisation in Slightly Sour Gas/Condensate Pipelines. *Corrosion NACEExpo 2006*. Houston: Nace International.
- Landolt, D. (2006). *Corrosion and Surface Chemistry of Metals*. (2<sup>nd</sup> ed). Switzerland: EPFL Press.
- Mercer, A. D. (1988). *Chemical Inhibitors for Corrosion Control*. (1<sup>st</sup> ed). Manchester: Royal Society of Chemistry.
- Okafor, P. C., Ikpi, M. E., Uwah, I. E., Ebenso, E. E., Ekpe, U. J. and Umoren, S. A. (2008). Inhibitory Action of Phyllanthus amarus Extracts on the Corrosion of Mild Steel in Acidic Media. *Corrosion Science*. 50: 2310-2317.
- Perez, N. (2004). *Electrochemistry and Corrosion Science*. (1<sup>st</sup> ed). USA: Kluwer Academic Publishers.

- Rehim, S. S. A., Hazzazi, O. A., Amin, M. A. and Khaled, K. F. (2008). On the Corrosion Inhibition of Low Carbon Steel in Concentrated Sulphuric Acid Solutions. Part I: Chemical and Electrochemical (AC and DC) Studies. *Corrosion Science*. 50: 2258-2271.
- Rim-Rukeh, Akpofure, Awatefe and Kehinde, J. (2006). Investigation of Soil Corrosivity in the Corrosion of Low Carbon Steel Pipe in Soil Environment. *Journal of Applied Sciences Research*. 2: 466-469.
- Samide, A., Bibicu, I., Rogalski, M. and Preda, M. (2004). A Study of the Corrosion Inhibition Of Carbon-Steel In Dilluted Ammonia Media using 2-mercapto-benzothiazol (MBT). *Acta Chim. Slov*. 51: 127-136.
- Samide, A., Bibicu, I., Rogalski, M. S. and Preda, M. (2005). Study of the Corrosion Inhibition of Carbon-Steel in Dilute Ammoniacal Media using N-ciclohexil-benzothiazole-sulphenamida. *Corrosion Science*. 47: 1119-1127.
- Samide, A. P., Bibicu, I., Agiu, M. and Preda, M. (2008). Mössbauer Spectroscopy Study on the Corrosion Inhibition of Carbon Steel in Hydrochloric Acid Solution. *Materials Letters*. 62: 320-322.
- Samiento-Bustos, E., Rodriguez, J. G. G., Uruchurtu, J., Dominguez-Patiño, G. and Salinas-Bravo, V. M. (2008). Effect of Inorganic Inhibitors on the Corrosion Behavior of 1018 Carbon Steel in the LiBr + Ethylene Glycol + H<sub>2</sub>O Mixture. *Corrosion Science*. 50: 2296-2303.
- Sarmiento, E., Gonzalez-Rodriguez, J. G. and Uruchurtu, J. (2008). A Study of the Corrosion Inhibition of Carbon Steel in a Bromide Solution using Fractal Analysis. *Surface & Coatings Technology*. 22: 175-183.
- Scendo, M. (2005a). Corrosion Inhibition of Copper by Pottasium Ethyl Xanthate in Acidic Chloride Solution. *Corrosion Science*. 47: 2778-2791.
- Scendo, M. (2005b). Pottasium Ethyl Xanthate as Corrosion Inhibitor for Copper in Acidic Chloride Solutions. *Corrosion Science*. 47: 1738-1749.
- Scendo, M. (2007). The Effect of Purine on the Corrosion of Copper in Chloride Solutions. *Corrosion Science*. 49: 373-390.
- Scendo, M. and Hepel, M. (2007). Inhibiting Properties of Benzimidazole Films for Cu(II)/Cu(I) Reduction in Chloride Media Studied by RDE and EQCN Techniques. *Corrosion Science*. 49: 3381-3407.

- Tang, L., Li, X., Mu, G., Li, L. and Liu, G. (2006). Synergistic Effect between 4-(2-pyridylazo) resorcin and Chloride Ion on the Corrosion of Cold Rolled Steel in 0.5M Sulfuric Acid. *Applied Surface Science*. 252: 6394-6401.
- Telegdi, J., Shaban, A. and Kalman, E. (2000). EQCM Study of Copper and Iron Corrosion Inhibition in Presence of Organic Inhibitors and Biocides. *Electrochimica Acta*. 45: 3639-3647.
- Thompson, N. G. (2001). *Gas Distribution. Corrosion Costs and Preventive Strategies in the United States*. USA: CC Technologies Services, Inc.
- Trachli, B., Keddami, M., Takenouti, H. and Shiri, A. (2002). Protective Effect of Electropolymerized 3-amino 1,2,4-triazole Towards Corrosion of Copper in 0.5 M NaCl. *Corrosion Science*. 44: 997-1008.
- Treseder, R. S. (1991). *The NACE Corrosion Engineer's Reference Book*. (1<sup>st</sup> ed). Texas: National Association of Corrosion Engineers.
- Tuomi, D. (1979). *Corrosion: Corrosion Chemistry*. (1<sup>st</sup> ed). Washington D.C.: American Chemical Society.
- Umoren, S. A., Ogbobe, O., Igwe, I. O. and Ebenso, E. E. (2008). Inhibition of Mild Steel Corrosion in Acidic Medium using Synthetic and Naturally Occurring Polymers and Synergistic Halide Additives. *Corrosion Science*. 50: 1998-2006.
- Walter, G. W. (1996). A Review of Impedance Plot Methods Used for Corrosion Performance Analysis of Painted Metals. *Corrosion Science*. 26: 681-703.
- Wranglen, G. (1972). *An Introduction to Corrosion and Protection of Metals*. (1<sup>st</sup> ed). Stockholm: Butler & Tanner Ltd.



Triazoles are an important class of heterocycles with numerous applications as pharmaceuticals, agrochemicals, corrosion inhibitors, dyestuffs, optical brighteners, fluorescent whiteners, photostabilizers of polymers, and photographic photoreceptors. From: The Chemistry of Heterocycles, 2019. Related terms thiazole 1,3-thiazole. 5 N2. N H. / Triazoles and its derivatives. 43. N. Application of crown ethers may take place in organic chemistry by dissolution of a crown ether in aprotic solvent, then adding potassium, or sodium salts to it, the crown ether makes complex with the cation, and precipitated. There is a highly reactive anion in the solution after filtration. E.g., potassium permanganate becomes soluble in benzene after treating it with crown ether, then this apolar solution of permanganate anion is used as strong oxidizing agent. The number of novel N-heterocyclic moieties with significant physiological properties and promising applications in medicinal chemistry is ever-growing. In this review, we consolidate the recent advances on novel nitrogen-containing heterocycles and their distinct biological activities, reported over the past one year (2019 to early 2020). This review highlights the trends in the use of nitrogen-based moieties in drug design and the development of different potent and competent candidates against various diseases. Epidemiologia Epigenomes European Burn Journal (EBJ) European Journal of Investigation in Health, Psychology and Education (EJIHPE) Fermentation Fibers Fire Fishes Fluids Foods Forecasting Forensic Sciences Forests Fractal and Fractional This review described triazole and tetrazole (five-ring), these are heterocyclic aromatic five-ring compounds consisting of (two carbon atoms and three nitrogen atoms in triazole) while (four nitrogen atoms with one carbon atom in tetrazole), and they exist in three different formulas with different locations of heterogeneous atoms in the ring. These compounds were distinguished by a high efficiency towards microorganisms and microbes and have wide importance in the field of biochemistry and are considered a basic nucleus in many compounds Life as well in pharmacological drugs, and the present ... biological applications of thiazole derivatives. Thiazole, any of a class of organic compounds of the heterocyclic series characterized by a ring structure composed of three carbon atoms, one nitrogen atom, and one sulfur atom. This ring structure occurs in such important biologically active natural products as thiamine (vitamin B1), bacitracin. Other thiazole compounds include rhodanine and the dye rhodanine red derived from it, and the yellow dye primuline. Synthetic drugs belonging to the thiazole family include sulfathiazole, sulfasuxidine, and thiazolsulfone (Promizole). 2-Mercaptobenzothiazole (Mertax) is a thiazole derivative used for accelerating the vulcanization of rubber. Learn More in these related Britannica articles: heterocyclic compound: Five- and six-membered rings with two or more heteroatoms.